

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Remanufacturing

Industry: Air pollution control

Segment: 01 Auto Maintenance

Soil: Baked on carbon

Substrate: Steel, stainless steel

Description of Part(s): Stainless steel filter mesh in a steel housing.

Customer objective: The customer was looking to improve their cleaning performance, automate their cleaning process and reduce rework and reject rate.

Cleaner used: 5% by volume ArmaKleen™ 4 in 1 Cleaner

Machine used: Ultrasonic Washer (SK 6315)

Temperature used: 160°F

Time required: 4 hours

Post Cleaning: Fresh water rinse followed by air pressure drying.

Recommendation to Customer: The ArmaKleen Technical Center recommended using 5% by volume ArmaKleen™ 4 in 1 Cleaner at 160°F in an Ultrasonic Washer for a minimum of 4 hours.

Before Picture



After Picture

