

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Paint & Ink

Industry: Automotive

Segment: Auto Maintenance

Soil: Sand/resin

Substrate: Brass

Description of Part(s): Filters

Customer objective: Improve cleaning performance

Cleaner used: 100% by volume solution of ArmaKleen™ Paint & Ink Remover

Machine used: Ultrasonic Washer (SK Blackstone 6315)

Temperature used: 160°F

Time required: 4-16 hours

Post Cleaning: Fresh water rinse and air pressure dried

Recommendation to Customer: The ArmaKleen Technical Center recommends using a 100% by volume solution of ArmaKleen™ Paint and Ink Remover at 160°F in an Ultrasonic Washer) for a minimum of 4-16 hours

Before Picture



After Picture



Source: TSR #18-P-139