

## ***ArmaKleen Technical Service Report Summary***

**Cleaning Trial Type:** Paint & Ink

**Industry:** Car Maintenance

**Segment:** Auto Maintenance

**Soil:** Furnace sand

**Substrate:** Copper/brass

**Description of Part(s):** Filter

**Customer objective:** Improve cleaning performance

**Cleaner used:** 100% by volume solution of ArmaKleen™ Paint & Ink Remover

**Machine used:** Ultrasonic Washer (SK Blackstone 6315)

**Temperature used:** 160°F

**Time required:** 16 hours

**Post Cleaning:** Fresh water rinse and air pressure dried

**Recommendation to Customer:** The ArmaKleen Technical Center recommends using a 100% by volume solution of ArmaKleen™ Paint and Ink Remover at 160°F in an Ultrasonic Washer for a minimum of 16 hours

**Before Picture**



**After Picture**



**Source:** TSR #18-P-153