

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Paint & Ink

Industry: Marine

Segment: 2 – Auto Retail

Soil: Shop dirt, oil, grime, epoxy e-coat paint, liquid urethane paint

Substrate: Steel, aluminum, copper/brass

Description of Part(s): Marine engine parts

Customer objective: Improve cleaning performance, automate cleaning process, reduce rework and reject rate, clean mixed metals together, and reduce cleaning costs

Cleaner used: 100% by volume solution of ArmaKleen™ Paint & Ink Remover

Machine used: Spray Under Immersion Washer (SK Model 81.8, Graymills T12, Graymills T24 w/ SUI)

Temperature used:

- 150°F
- 160°F

Time required: 4-8 hours

Post Cleaning: Fresh water rinse and air pressure drying

Recommendation to Customer: The ArmaKleen Technical Center recommends using a 100% by volume solution of ArmaKleen™ Paint and Ink Remover at 150°F-160°F in a Spray-Under Immersion Washer for a minimum of 4-8+ hours

Before Picture



After Picture



Source: TSR #17-P-176