

## ***ArmaKleen Technical Service Report Summary***

**Cleaning Trial Type:** Paint & Ink

**Industry:** Coatings Manufacturing

**Segment:** Chemical Manufacturing

**Soil:** Sealant, glue/adhesive, epoxy e-coat paint

**Substrate:** Stainless steel, steel

**Description of Part(s):** Pipes, connectors, and a blade

**Customer objective:** Improve cleaning performance, automate cleaning process

**Cleaner used:** 100% by volume solution of ArmaKleen™ Paint & Ink Remover

**Machine used:** Spray Under Immersion Washer (Graymills T12, Graymills T24, SK Model 81.8 w/ SUI)

**Temperature used:** 160°F

**Time required:** 8 hours

**Post Cleaning:** All threaded areas of the parts and several interiors were brushed with a stainless steel bristle brush during the fresh water rinse and air pressure dried

**Recommendation to Customer:** The ArmaKleen Technical Center recommends using a 100% by volume solution of ArmaKleen™ Paint and Ink Remover at 150°F in a Spray-Under Immersion Washer for a minimum of 8+ hours

**Before Picture**



**After Picture**



**Source:** TSR #18-P-098