

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Aqueous

Industry: Chemicals Manufacturing

Segment: 21 Chemical Manufacturing

Soil: Calcified lime

Substrate: Stainless steel

Description of Part(s): Discs

Customer objective: Improve cleaning performance, automate cleaning process, reduce cleaning costs

Cleaner used: 10% by volume ArmaKleen™ Rust Remover

Machine used: Ultrasonic Washer (SK Blackstone 6315)


Temperature used: 160°F

Time required: 30 minutes

Post Cleaning: Fresh water rinse and air pressure dried

Recommendation to Customer: The ArmaKleen Technical Center recommends using a 10% by volume solution of ArmaKleen™ Rust Remover at 160°F in a Ultrasonic Washer for a minimum of 30 minutes

Before Picture



After Picture



Source: TSR #19-A-016