

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Adhesive removal

Industry: Manufacturing

Segment: 21 Chemical Manufacturing

Soil: Glue/adhesive

Substrate: Aluminum

Description of Part(s): Aluminum bracket

Customer objective: The customer was looking to improve their cleaning performance, eliminate hazardous chemicals and waste and reduce VOCs.

Cleaner used: 100% by volume ArmaKleen™ Paint and Ink Remover

Machine used: Ultrasonic Washer (SK Blackstone model 6315)

Temperature used: 160°F

Time required: 1 hour

Post Cleaning: Fresh water rinse followed by air pressure drying

Recommendation to Customer: The ArmaKleen Technical Center recommended using 100% by volume ArmaKleen™ Paint and Ink Remover at 160°F in an Ultrasonic Washer for a minimum of 1 hour.

Before Picture



After Picture

