

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Aqueous

Industry: Paint Manufacturing

Segment: Chemical - Distributor

Soil: Oil

Substrate: Steel

Description of Part(s): Shafts

Customer objective: Improve cleaning performance

Cleaner used: 5% by volume solution of ArmaKleen™ 4 in 1 Cleaner

Machine used:

- Spray Washer (JRI FL 250, JRI FL 500, JRI TL 500)
- Spray Under Immersion Washer (Graymills T12, Graymills T24, SK Model 81.8 w/ SUI)

Temperature used:

- 160°F
- 150°F

Time required: 1 hour

Post Cleaning: Fresh water rinse and air pressure dried

Recommendation to Customer: The ArmaKleen Technical Center recommends using a 5% by volume solution of ArmaKleen™ 4 in 1 Cleaner at 160°F in a Spray Washer or at 150°F in a Spray-Under Immersion Washer (Model 81.8 with attached spray pump) for a minimum of 15 minutes to 1 hour.

Before Picture



After Picture



Source: TSR #18-A-003