

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Aqueous

Industry: Styrenics

Segment: 22 Chemical Distributor

Soil: Grime, baked on carbon, rust/oxides

Substrate: Stainless steel

Description of Part(s): assortment of nozzles and connectors

Customer objective: Clean mixed metals together and recover scrap parts

Cleaner used: 10% by volume ArmaKleen™ M-100 BCR

Machine used: Agitating Immersion Washer (Graymills T12, Graymills T24, SK Model 81.8)

Temperature used: 150°F

Time required: 14-24 hours

Post Cleaning: Fresh water rinse and air pressure dried

Recommendation to Customer: The ArmaKleen Technical Center recommends using a 10% by volume of ArmaKleen™ M-100 BCR at 150°F in an Agitating Immersion Washer for a minimum of 24 hours

Before Picture



After Picture



Source: TSR #19-A-117