

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Aqueous

Industry: Electrical Motors Manufacturing

Segment: Electrical Equipment & Computers Manufacturing

Soil: Shop dirt

Substrate: Stainless steel

Description of Part(s): Gears

Customer objective: Change the footprint of the space a washer takes up in the customer's facility

Cleaner used: 10% by volume solution of ArmaKleen™ M-Aero

Machine used: Spray Washer (JRI FL 250, JRI FL 500, JRI TL 3)

Temperature used: 160°F

Time required: 15-30 minutes

Post Cleaning: Fresh water rinse and air pressure dried

Recommendation to Customer: The ArmaKleen Technical Center recommends using a 10% by volume solution of ArmaKleen™ M-Aero at 160°F in a Spray Washer for a minimum of 15-30 minutes

Before Picture



After Picture



Source: TSR #18-A-180