

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Aqueous

Industry: Manufacturing

Segment: 26 – Fabricated Metal Products

Soil: Shop dirt, oil, glue/adhesive, grime, grease

Substrate: Rubber, steel

Description of Part(s): Rubber spacers

Customer objective: The customer was looking to automate their cleaning process.

Cleaner used: 100% by volume ArmaKleen™ Paint and Ink Remover

Machine used: Agitating Immersion Washer (SK 81.8, Graymills T12, Graymills T24)

Temperature used: 150°F

Time required: 2 hours

Post Cleaning: Lightly wiped during the fresh water rinse followed by air pressure drying.

Recommendation to Customer: The ArmaKleen Technical Center recommended using 100% by volume ArmaKleen™ Paint and Ink Remover at 150°F in an Agitating Immersion Washer for a minimum of 2 hours.

Before Picture



After Picture



Source: TSR #15-PA-180