

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Aqueous

Industry: Exhaust and emission system Manufacturer

Segment: 26 – Fabricated Metal Products

Soil: oil and grease

Substrate: Steel, stainless steel

Description of Part(s): One steel elbow pipe

Customer objective: The customer was looking to improve their cleaning performance and automate their cleaning process

Cleaner used: 5% by volume solution of ArmaKleen™ 4 in 1 Cleaner

Machine used: Agitating Immersion Washer (SK Model 81.8, Graymills T24)


Temperature used: 150°F

Time required: 30 minutes

Post Cleaning: Fresh water rinse followed by air pressure drying

Recommendation to Customer: The ArmaKleen Technical Center recommends using a 5% by volume solution of ArmaKleen™ 4 in 1 Cleaner at 150°F in an Agitating Immersion Washer for a minimum of 30 minutes

Before Picture



After Picture



Source: TSR #16-A-087