

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Aqueous

Industry: Rubber Supplier

Segment: 26 Fabricated Metal Products

Soil: Oil, rust/oxides

Substrate: Aluminum

Description of Part(s): Assortment of tubes and brackets

Customer objective: Improve cleaning performance, automate cleaning process, reduce rework and reject rate, recover scrap parts

Cleaner used: 10% by volume ArmaKleen™ M-Aero

Machine used: Spray Washer (JRI FL 250, JRI FL 500, JRI TL 3)

Temperature used: 160°F

Time required: 15-30 minutes

Post Cleaning: Fresh water rinse and air pressure dried

Recommendation to Customer: The ArmaKleen Technical Center recommends using a 10% by volume solution of ArmaKleen™ M-Aero at 160°F in a Spray Washer for a minimum of 15-30 minutes

Before Picture



After Picture



Source: TSR #19-A-050