

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Paint & Ink

Industry: Connectors Manufacturing

Segment: 26 Fabricated Metal Products

Soil: Glue/adhesive

Substrate: Steel/iron, stainless steel, aluminum

Description of Part(s): Pipe fittings

Customer objective: Improve cleaning performance, automate cleaning process, eliminate hazardous chemicals/waste, reduce VOCs

Cleaner used: 100% by volume ArmaKleen™ Paint & Ink Remover

Machine used: Ultrasonic Washer (SK Blackstone 6315)

Temperature used: 160°F

Time required: 8 hours

Post Cleaning: Fresh water rinse and air pressure dried

Recommendation to Customer: The ArmaKleen Technical Center recommends using a 100% by volume solution of ArmaKleen™ Paint & Ink Remover at 150°F in a Spray Under Immersion Washer for a minimum of 8+ hours

Before Picture



After Picture



Source: TSR #19-P-043