

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Aqueous

Industry: Appliance Servicing

Segment: Fabricated Metals

Soil: Oil, grime, grease, baked on carbon

Substrate: Steel

Description of Part(s): Rims

Customer objective: Improve cleaning performance, eliminate hazardous waste/chemicals

Cleaner used: 10% by volume solution of ArmaKleen™ M-100 BCR

Machine used: Spray Washer (JRI FL 250, JRI FL 500, JRI TL 3)

Temperature used: 160°F

Time required: 15-30 minutes

Post Cleaning: Several areas wiped with a clean cotton cloth during the fresh water rinse and air pressure dried

Recommendation to Customer: The ArmaKleen Technical Center recommends using a 10% by volume solution of ArmaKleen™ M-100 BCR at 160°F in a Spray Washer for a minimum of 15-30 minutes

Before Picture



After Picture



Source: TSR #18-A-073