

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Paint & Ink

Industry: Cabinet Manufacturer

Segment: 27 – Mfg – Furniture, Millwork, Cabinets & Fixtures

Soil: liquid acrylic paint

Substrate: Steel

Description of Part(s): two steel brackets/poles

Customer objective: The customer was looking to improve their cleaning performance.

Cleaner used: 100% by volume solution of ArmaKleen™ Paint and Ink Remover

Machine used: Spray Under Immersion Washer (Graymills T12, Graymills T24, SK Model 81.8 w/SUI)

Temperature used: 150°F

Time required: 8-16 hours

Post Cleaning: Several areas of nuts and bolts were lightly brushed with a stainless steel bristle brush during the fresh water rinse and then air pressure dried.

Recommendation to Customer: The ArmaKleen Technical Center recommends using a 100% by volume solution of ArmaKleen™ Paint and Ink Remover at 150°F in a Spray-Under Immersion Washer for a minimum of 8-16 hours.

Before Picture



After Picture



Source: TSR #16-P-083