

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Ink Removal

Industry: Printing

Segment: 28 MFG – Machine (Including Medical)

Soil: Ink and toner

Substrate: Steel

Description of Part(s): steel augers

Customer objective: The customer was looking to automate their cleaning process, reduce rework and reject rate, eliminate hazardous chemicals and waste and reduce VOCs.

Cleaner used: 100% by volume ArmaKleen™ Paint and Ink Remover

Machine used: Ultrasonic Washer (SK 6315 Blackstone Model 3523)

Temperature used: 160°F

Time required: 30 minutes to 4 hours

Post Cleaning: Fresh water rinse followed by air pressure drying

Recommendation to Customer: The ArmaKleen Technical Center recommended using 100% by volume ArmaKleen™ Paint and Ink Remover at 160°F in an Ultrasonic Washer for a minimum of 30 minutes to 4 hours.

Before Picture



After Picture

