

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Paint & Ink

Industry: Power Tool Manufacturer

Segment: 28 – Mfg – Machine (incl Medical)

Soil: baked on enamel coat paint

Substrate: Steel

Description of Part(s): an assortment of steel hole-dozers (2.1/8" circular cutting blades)

Customer objective: The customer was looking to improve their cleaning performance, automate their cleaning process, reduce rework and reject rate and reduce their cleaning costs

Cleaner used: 100% by volume solution of ArmaKleen™ Paint and Ink Remover

Machine used: Ultrasonic Washer (SK Blackstone 6315)

Temperature used: 160°F

Time required: 30 minutes

Post Cleaning: Fresh water rinse followed by air pressure drying

Recommendation to Customer: The ArmaKleen Technical Center recommends using a 100% by volume solution of ArmaKleen™ Paint and Ink Remover at 160°F in an Ultrasonic Washer for a minimum of 30 minutes

Before Picture



After Picture



Source: TSR #16-P-035