

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Aqueous

Industry: Diesel Engine Manufacturer

Segment: 28 – Mfg – Machine (incl Medical)

Soil: oil, grease and Loctite Adhesive

Substrate: Steel, Stainless Steel, Aluminum, Brass

Description of Part(s): an assortment of steel, stainless steel, aluminum and brass engine parts

Customer objective: The customer was looking to automate their cleaning process

Cleaner used: 5% by volume solution of ArmaKleen™ 4 in 1 Cleaner

Machine used: Spray Washer (JRI TL3, JRI FL250, JRI FL500, Better Engineering G-2000)

Temperature used: 160°F

Time required: 15-30+ minutes

Post Cleaning: Fresh rinse followed by air pressure drying

Recommendation to Customer: The ArmaKleen Technical Center recommends using a 5% by volume solution of ArmaKleen™ 4 in 1 Cleaner at 160°F in a Spray Washer for a minimum of 15-30+ minutes.

Before Picture



After Picture



Source: TSR #17-A-086