

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Paint & Ink

Industry: Remanufacturing

Segment: 28 Mfg – Machine (Including Medical)

Soil: Polyester powder coat paint

Substrate: Silicone

Description of Part(s): An assortment of silicone dispensers and connectors

Customer objective: Improve cleaning performance

Cleaner used: 100% by volume solution of ArmaKleen™ Paint & Ink Remover

Machine used: Agitating Immersion Washer (Gramills T12, Graymills T24, SK Model 81.8)

Temperature used: 150°F

Time required: Minimum of 2 to 4 hours

Post Cleaning: Fresh water rinse and air pressure drying; several areas on many parts were wiped with a cotton cloth during fresh water rinse, while other parts were brushed with a nylon bristle brush

Recommendation to Customer: The ArmaKleen Technical Center recommends using a 100% by volume solution of ArmaKleen™ Paint and Ink Remover at 150°F in an Agitating Immersion Washer (Model 81.8) for a minimum of 2-4+ hours.

Before Picture



After Picture



Source: TSR# 17-P-164