

## ***ArmaKleen Technical Service Report Summary***

**Cleaning Trial Type:** Paint & Ink

**Industry:** Machinery manufacturing

**Segment:** 28 – Mfg – Machine (Incl Medical)

**Soil:** Liquid acrylic paint

**Substrate:** Steel

**Description of Part(s):** Paint hooks

**Customer objective:** Improve cleaning performance, automate cleaning process, reduce rework and reject rate, reduce cleaning costs, eliminate hazardous chemicals/waste

**Cleaner used:** 100% by volume solution of ArmaKleen™ Paint & Ink Remover

**Machine used:** Ultrasonic Washer (SK Blackstone 6315)

**Temperature used:** 160°F

**Time required:** 8 hours

**Post Cleaning:** Fresh water rinse and air pressure drying

**Recommendation to Customer:** The ArmaKleen Technical Center recommends using a 100% by volume solution of ArmaKleen™ Paint and Ink Remover at 160°F in an Ultrasonic Washer for a minimum of 8 hours

**Before Picture**



**After Picture**



**Source:** TSR #17-P-207