

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Aqueous

Industry: Welding Products

Segment: Machine (Including Medical) Manufacturing

Soil: Shop dirt, oil, cutting fluids

Substrate: Copper, stainless steel

Description of Part(s): Connectors

Customer objective: Improve cleaning performance, automate cleaning process, reduce cleaning costs

Cleaner used: 5% by volume solution of ArmaKleen™ BIO-24

Machine used: Spray Under Immersion (Graymills T12, Graymills T24, SK Model 81.8 w/ SUI)

Temperature used: 150°F

Time required: 30 minutes to 1 hour

Post Cleaning: Fresh water rinse and air pressure dried

Recommendation to Customer: The ArmaKleen Technical Center recommends using a 5% by volume solution of ArmaKleen™ Bio 24 at 150°F in a Spray-Under Immersion Washer for a minimum of 30 minutes to 1 hour

Before Picture



After Picture

