

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Paint removal

Industry: OEM Painting

Segment: 28 – Manufacturing – Machine including Medical

Soil: Two part liquid epoxy paint

Substrate: Plastic, steel and aluminum

Description of Part(s): Plastic and aluminum wheel/roller and steel spray gun pump

Customer objective: The customer was looking to improve their cleaning performance and eliminate hazardous chemicals and waste.

Cleaner used: 100% by volume ArmaKleen™ Paint and Ink Remover

Machine used: Spray Under Immersion Washer (Graymills T12, Graymills T24, SK 81.8 w/SUI)

Temperature used: 160°F

Time required: 2 – 6 hours

Post Cleaning: Fresh water rinse with light brushing with a nylon bristle brush followed by air pressure drying.

Recommendation to Customer: The ArmaKleen Technical Center recommended using 100% by volume ArmaKleen™ Paint and Ink Remover at 160°F in a Spray Under Immersion Washer for a minimum of 2 hours.

Before Picture



After Picture

