

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Adhesive Removal

Industry: Manufacturing

Segment: 28 – Manufacturing – Machine (including Medical)

Soil: Glue/adhesive

Substrate: Steel, brass

Description of Part(s): Elbow pipes and brackets

Customer objective: The customer was looking to improve their cleaning performance and recover scrap parts.

Cleaner used: 100% by volume ArmaKleen™ Paint and Ink Remover

Machine used:

1. Agitating Immersion Washer (SK 81.8, Graymills T12, Graymills T24)
2. Spray Under Immersion Washer (Graymills T12, Graymills T24, SK 81.8 w/SUI)

Temperature used: 150°F – 160°F

Time required: 24 hours

Post Cleaning: Interior & exterior of the part was brushed with a stainless steel bristle brush during the fresh water rinse followed by air pressure drying.

Recommendation to Customer: The ArmaKleen Technical Center recommended using 100% by volume ArmaKleen™ Paint and Ink Remover at 150°F in an Agitating Immersion Washer or at 160°F in a Spray Under Immersion Washer for a minimum of 24+ hours.

Before Picture



After Picture

