

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Aqueous

Industry: Security and Surveillance Tech

Segment: 29 – Mfg – Miscellaneous

Soil: Cutting fluids

Substrate: Aluminum

Description of Part(s): Four aluminum electrical boxes/frames

Customer objective: The customer was looking to improve their cleaning performance and automate their cleaning process.

Cleaner used: 10% by volume solution of ArmaKleen™ MM-Recycle

Machine used: Spray Under Immersion Washer (Graymills T12, Graymills T24, SK Model 81.8 w/SUI)

Temperature used: 160°F

Time required: 4 – 8 minutes

Post Cleaning: Air pressure dried

Recommendation to Customer: The ArmaKleen Technical Center recommends using a 10% by volume solution of ArmaKleen™ MM-Recycle at 160°F in a Spray-Under Immersion Washer for a minimum of 4 minutes to 8 minutes

Before Picture



After Picture



Source: TSR #16-A-096