

## ***ArmaKleen Technical Service Report Summary***

**Cleaning Trial Type:** Adhesive removal

**Industry:** Printing

**Segment:** 29 – Manufacturing – Miscellaneous

**Soil:** Adhesive, UV Ink

**Substrate:** Aluminum

**Description of Part(s):** Print frame

**Customer objective:** The customer was looking to improve their cleaning performance, automate their cleaning process, eliminate hazardous chemicals and waste and reduce VOCs.

**Cleaner used:** 100% by volume ArmaKleen™ Paint and Ink Remover

**Machine used:** Agitating Immersion Washer (SK 81.8, Graymills T12, Graymills T24)

**Temperature used:** 150°F

**Time required:** 15 to 45 minutes

**Post Cleaning:** Wiped with a clean cotton cloth during the fresh water rinse followed by air pressure drying.

**Recommendation to Customer:** The ArmaKleen Technical Center recommended using 100% by volume ArmaKleen™ Paint and Ink Remover at 150°F in an Agitating Immersion Washer for a minimum of 15 – 45 minutes.

**Before Picture**



**After Picture**

