

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Aqueous

Industry: Electronic parts supplier

Segment: 29 – Mfg – Miscellaneous

Soil: oil, cutting fluids and grease

Substrate: Steel

Description of Part(s): seven steel bars

Customer objective: The customer was looking to improve their cleaning performance.

Cleaner used: 5% by volume solution of ArmaKleen™ 4 in 1 Cleaner

Machine used:

- Spray Under Immersion Washer (Graymills T12, Graymills T24, SK Model 81.8 w/SUI)
- Spray Washer (JRI TL3, JRI FL250, JRI FL500, Better Engineering G-2000)

Temperature used: 150°F

Time required: 15-30 minutes

Post Cleaning: Fresh water rinse followed by air pressure drying

Recommendation to Customer: The ArmaKleen Technical Center recommends using a 5% by volume solution of ArmaKleen™ 4 in 1 Cleaner at 150°F in a Spray-Under Immersion Washer or at 160°F in a Spray Washer for a minimum of 15-30 minutes.

Before Picture



After Picture



Source: TSR #17-A-137