

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Paint & Ink

Industry: Engineering

Segment: Miscellaneous Manufacturing

Soil: Unknown paint

Substrate: Steel

Description of Part(s): Paint hooks

Customer objective: Eliminate use of outside stripping vendor

Cleaner used: 100% by volume solution of ArmaKleen™ Paint & Ink Remover

Machine used:

- Agitating Immersion Washer (Graymills T12, Graymills T24, SK Model 81.8)
- Ultrasonic Washer (SK Blackstone 6315)

Temperature used: 160°F

Time required: 8-12 hours

Post Cleaning: Several areas (bent areas of hooks) were lightly brushed with a stainless steel bristle brush during fresh water rinse and air pressure dried

Recommendation to Customer: The ArmaKleen Technical Center recommends using a 100% by volume solution of ArmaKleen™ Paint and Ink Remover at 160°F in an Agitating Immersion Washer (Model 81.8) for a minimum of 8-12 hours or a 100% by volume solution of ArmaKleen™ Paint and Ink Remover at 160°F in an Ultrasonic Washer for 12 hours.

Before Picture



After Picture



Source: TSR #18-P-007