

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Paint & Ink

Industry: Gaming Machines Manufacturing

Segment: Miscellaneous Manufacturing

Soil: Unknown glue/adhesive

Substrate: Stainless steel

Description of Part(s): Filter w/ inside meshing

Customer objective: Improve cleaning performance, reduce rework and reject rate, recover scrap parts

Cleaner used: 100% by volume solution of ArmaKleen™ Paint & Ink Remover

Machine used: Ultrasonic Washer (SK Blackstone 6315)

Temperature used: 160°F

Time required: 5 hours

Post Cleaning: Interior of stainless steel mesh brushed during the fresh water rinse and air pressure dried

Recommendation to Customer: The ArmaKleen Technical Center recommends using a 100% by volume solution of ArmaKleen™ Paint and Ink Remover at 160°F in an Ultrasonic Washer for a minimum of 8 hours

Before Picture



After Picture



Source: TSR #18-P-096