

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Paint & Ink

Industry: Bathroom Equipment Manufacturing

Segment: 29 Miscellaneous Manufacturing

Soil: Glue/adhesive, wax

Substrate: Steel/iron

Description of Part(s): Processing equipment parts

Customer objective: Improve cleaning performance, automate cleaning process, eliminate hazardous chemicals/waste, reduce VOCs

Cleaner used: 100% by volume ArmaKleen™ Paint & Ink Remover

Machine used:

- Spray Under Immersion Washer (Graymills T12, Graymills T24, SK Model 81.8 w/ SUI)
- Ultrasonic Washer (SK Blackstone 6315)

Temperature used:

- 150°F
- 160°F

Time required: 6-8 hours

Post Cleaning: Fresh water rinse and air pressure dried

Recommendation to Customer: The ArmaKleen Technical Center recommends using a 100% by volume solution ArmaKleen™ Paint and Ink Remover at 150°F in an Ultrasonic Washer for a minimum of 8+ hours

Before Picture



After Picture



Source: TSR #19-P-047