

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Paint & Ink

Industry: Steel Working

Segment: Primary Metal Manufacturing

Soil: UV ink (QUAKERCOAT® 038)

Substrate: Brass

Description of Part(s): Small spray nozzle

Customer objective: Improve cleaning performance, automate cleaning process

Cleaner used: 100% by volume solution of ArmaKleen™ Paint & Ink Remover

Machine used: Ultrasonic Washer (SK Blackstone 6315)

Temperature used: 160°F

Time required: 2 hours

Post Cleaning: Fresh water rinse and air pressure dried

Recommendation to Customer: The ArmaKleen Technical Center recommends using a 100% by volume solution of ArmaKleen™ Paint and Ink Remover at 160°F in an Ultrasonic Washer for a minimum of 2 hours

Before Picture



After Picture



Source: TSR #18-P-151