

## ***ArmaKleen Technical Service Report Summary***

**Cleaning Trial Type:** Paint & Ink

**Industry:** Marble Manufacturing

**Segment:** 34 Non-Metal (Plastic, Rubber, Glass) Manufacturing

**Soil:** Acrylic powder coat paint, liquid acrylic paint, liquid alkyd paint

**Substrate:** Steel/iron, aluminum

**Description of Part(s):** Process equipment fixtures

**Customer objective:** Improve cleaning performance and reduce cleaning costs

**Cleaner used:** 100% by volume ArmaKleen™ Paint & Ink Remover

**Machine used:** Agitating Immersion Washer (Graymills T12, Graymills T24, SK Model 81.8)

**Temperature used:** 150°F

**Time required:** 2 hours

**Post Cleaning:** Fresh water rinse and air pressure dried

**Recommendation to Customer:** The ArmaKleen Technical Center recommends using a 100% by volume solution ArmaKleen™ Paint & Ink Remover at 150°F in an Agitating Immersion Washer for a minimum of 2 hours

**Before Picture**



**After Picture**



**Source:** TSR #19-P-076