

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Paint & Ink

Industry: Rubber manufacturing

Segment: 34 – Mfg – Non-Metal (Plastic, Rubber, Glass)

Soil: Unknown silicone/rubber compound

Substrate: Steel (1144 stressproof)

Description of Part(s): Disks

Customer objective: Improve cleaning performance, reduce cleaning costs and recover scrap parts

Cleaner used: 100% by volume solution of ArmaKleen™ Paint & Ink Remover

Machine used:

- Spray Under Immersion Washer (SK Model 81.8, Graymills T12, Graymills T24 w/ SUI)
- Ultrasonic Washer (SK Blackstone 6315)

Temperature used: 160°F

Time required: 20-24 hours

Post Cleaning: Fresh water rinse and air pressure drying

Recommendation to Customer: The ArmaKleen Technical Center recommends using a 100% by volume solution of ArmaKleen™ Paint and Ink Remover at 160°F in an Ultrasonic Washer for a minimum of 20 hours

Before Picture



After Picture



Source: TSR #17-P-173