

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Aqueous

Industry: Drill and vibrator manufacturer

Segment: 34 – Mfg – Non-Metal (Plastic, Rubber, Glass)

Soil: Oil, grime, cutting fluids and grease

Substrate: Steel

Description of Part(s): Six steel connectors

Customer objective: The customer was looking to improve their cleaning performance and automate their cleaning process.

Cleaner used: 5% by volume solution of ArmaKleen™ 4 in 1 Cleaner

Machine used:

- Agitating Immersion (SK Model 81.8, Graymills T24)
- Ultrasonic Washer (SK Blackstone model 6315)

Temperature used: 150°F – 160°F

Time required: 15 minutes to 1 hour


Post Cleaning: Fresh rinse followed by air pressure drying .

Recommendation to Customer: The ArmaKleen Technical Center recommends using a 5% by volume solution of ArmaKleen™ 4 in 1 Cleaner at 150°F in an Agitating Immersion Washer for a minimum of 15 minutes to 1 hour.

Before Picture



After Picture



Source: TSR #17-A-109