

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Aqueous

Industry: Paperboard manufacturing

Segment: 42 Printing

Soil: Water based glue

Substrate: Stainless steel

Description of Part(s): Stainless steel rod

Customer objective: The customer was looking to improve their cleaning performance, automate their cleaning process and to reduce their cleaning costs.

Cleaner used: 5% by volume ArmaKleen™ 4 in 1 Cleaner

Machine used: Ultrasonic Washer (SK6315 Blackstone model 3523)

Temperature used: 160°F

Time required: 30 minutes

Post Cleaning: Fresh water rinse followed by air pressure drying.

Recommendation to Customer: The ArmaKleen Technical Center recommended using 5% by volume ArmaKleen™ 4 in 1 Cleaner at 160°F in an Ultrasonic Washer for a minimum of 30 minutes.

Before Picture



After Picture



Source: TSR #13-A-023