

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Aqueous and Paint & Ink

Industry: Wood Product Manufacturing

Segment: 43 – Lumber and Wood Products

Soil: Unknown glue/adhesive

Substrate: Aluminum

Description of Part(s): Aluminum blocks

Customer objective: Improve cleaning performance

Cleaner used:

- 5% by volume solution of ArmaKleen™ 4 in 1 Cleaner
- 100% by volume solution of ArmaKleen™ Paint & Ink Remover

Machine used: Agitating Immersion Washer (SK Model 81.8, Graymills T12, Graymills T24)

Temperature used: 150°F

Time required: 8 hours

Post Cleaning: Fresh water rinse and air pressure drying

Recommendation to Customer: The ArmaKleen Technical Center recommends using a 100% by volume solution of ArmaKleen™ Paint and Ink Remover at 150°F in an Agitating Immersion Washer for a minimum of 8+ hours

Before Picture



After Picture

