

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Paint & Ink

Industry: Engine Repair

Segment: Transportation Equipment Manufacturing

Soil: CHEMGLAZE M331

Substrate: Steel

Description of Part(s): 5-gallon can with lid

Customer objective: Improve cleaning performance, automate cleaning process, recover scrap parts

Cleaner used: 100% by volume solution of ArmaKleen™ Paint & Ink Remover

Machine used: Spray Washer (JRI FL 250, JRI FL 500, JRI TL 3)

Temperature used: 160°F

Time required: 1 hour

Post Cleaning: Several areas wiped with a clean cotton cloth during fresh water rinse and air pressure dried

Recommendation to Customer: The ArmaKleen Technical Center recommends using a 100% by volume solution of ArmaKleen™ Paint and Ink Remover at 160°F in a Spray Washer for a minimum of 1 hour

Before Picture



After Picture



Source: TSR #18-P-176