

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Aqueous

Industry: Automotive

Segment: 54 – Mfg – Transportation Equipment

Soil: Oil, wax

Substrate: Steel

Description of Part(s): Assortment of fasteners

Customer objective: Improve cleaning performance, reduce rework/reject rate

Cleaner used: 10% by volume solution of ArmaKleen™ M-100 BCR

Machine used: Spray Under Immersion (SK Model 81.8, Graymills T24 w/ SUI)

Temperature used: 160°F

Time required: 10 minutes

Post Cleaning: Fresh water rinse and air pressure drying

Recommendation to Customer: The ArmaKleen Technical Center recommends using a 10% by volume solution of ArmaKleen™ M-100 BCR at 160°F in a Spray-Under Immersion Washer for a minimum of 10 minutes

Before Picture



After Picture



Source: TSR #17-A-204