

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Paint & Ink

Industry: Automotive

Segment: 54 Transportation Equipment Manufacturing

Soil: Oil-based car paint

Substrate: Plastic

Description of Part(s): Car parts

Customer objective: Improve cleaning performance, reduce rework and reject rate, recover scrap parts

Cleaner used: 100% by volume ArmaKleen™ Paint & Ink Remover

Machine used:

- Spray Under Immersion Washer (Graymills T12, Graymills T24, SK Model 81.8 w/ SUI)
- Agitating Immersion Washer (Graymills T12, Graymills T24, SK Model 81.8)

Temperature used: 150°F

Time required: 15-30 minutes

Post Cleaning: Fresh water rinse and air pressure dried

Recommendation to Customer: The ArmaKleen Technical Center recommends using a 100% by volume of ArmaKleen™ Paint & Ink Remover at 150°F in an Agitating Immersion Washer for a minimum of 15 minutes

Before Picture



After Picture



Source: TSR #19-P-124