

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Paint & Ink

Industry: Air starter Manufacturer

Segment: 58 – Building Materials (excl Lumber Mills)

Soil: shop dirt, oil, grime, grease, epoxy e-coat paint and liquid acrylic paint

Substrate: Steel

Description of Part(s): two steel connectors

Customer objective: The customer was looking to automate their cleaning process.

Cleaner used: 100% by volume solution of ArmaKleen™ Paint and Ink Remover

Machine used: Spray Washer (JRI TL3, JRI FL250, JRI FL500, Better Engineering G-2000)

Temperature used: 160°F

Time required: 1-2 hours

Post Cleaning: Fresh water rinse and air pressure dried

Recommendation to Customer: The ArmaKleen Technical Center recommends using a 100% by volume solution of ArmaKleen™ Paint and Ink Remover at 160°F in a Spray Washer for a minimum of 1-2 hours.

Before Picture



After Picture



Source: TSR #17-P-141