

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Paint & Ink

Industry: Molding

Segment: 86 Entertainment & Recreation Services

Soil: Glue/adhesive, Epoxy E-coat Paint, Acrylic Powder Coat Paint, Screen Ink, Water-based Ink

Substrate: Rubber

Description of Part(s): Template/stencil

Customer objective: Improve cleaning performance, automate cleaning process, eliminate hazardous chemicals/waste

Cleaner used: 100% by volume ArmaKleen™ Paint & Ink Remover

Machine used: Spray Under Immersion Washer (Graymills T12, Graymilss T24, SK Model 81.8 w/ SUI)

Temperature used: 150°F

Time required: 30 minutes

Post Cleaning: Fresh water rinse and air pressure dried

Recommendation to Customer: The ArmaKleen Technical Center recommends using a 100% by volume solution of ArmaKleen™ Paint and Ink Remover at 150°F in a Spray-Under Immersion Washer for a minimum of 30 minutes

Before Picture



After Picture



Source: TSR #19-P-003