

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Coating Removal

Industry: Manufacturing

Segment: 90 - Real Estate & Developers

Soil: Solvent-based graphite coating

Substrate: Stainless steel

Description of Part(s): Dip pans

Customer objective: The customer was looking to improve their cleaning performance, automate their cleaning process and eliminate hazardous chemicals and waste.

Cleaner used: 100% by volume ArmaKleen™ Paint and Ink Remover

Machine used: Agitating Immersion Washer (SK 81.8, Graymills T12, Graymills T24)

Temperature used: 150°F

Time required: 4 to 12 hours

Post Cleaning: Fresh water rinse followed by air pressure drying.

Recommendation to Customer: The ArmaKleen Technical Center recommended using 100% by volume ArmaKleen™ Paint and Ink Remover at 150°F in an Agitating Immersion Washer for a minimum of 4 to 12 hours.

Before Picture



After Picture



Source: TSR #15-P-239