

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Aqueous

Industry: Large Vehicle Remanufacturing

Segment: 92 Warehousing & Related Services

Soil: Oil, grime, grease and asphalt

Substrate: Steel

Description of Part(s): Steel tire rods

Customer objective: The customer was looking to improve their cleaning performance.

Cleaner used: 5% by volume ArmaKleen™ 4 in 1 Cleaner

Machine used: Spray Washer (TL3, FL250, FL500)

Temperature used: 160°F

Time required: 30 to 60 minutes

Post Cleaning: Fresh water rinse followed by air pressure drying.

Recommendation to Customer: The ArmaKleen Technical Center recommended using 5% by volume ArmaKleen™ 4 in 1 Cleaner at 160°F in a Spray Washer for a minimum of 30 to 60 minutes.

Before Picture



After Picture



Source: TSR #13-A-015