

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Urethane removal

Industry: Consumer Product Manufacture

Segment: 93 – Retail Trade

Soil: Cured liquid urethane

Substrate: Steel, rubber

Description of Part(s): Dispensers, connectors

Customer objective: The customer was looking to improve their cleaning performance.

Cleaner used: 100% by volume ArmaKleen™ Paint and Ink Remover

Machine used: Spray Under Immersion Washer (Graymills T12, Graymills T24, SK 81.8 w/SUI)

Temperature used: 150°F

Time required: 4 to 16 hours

Post Cleaning: Fresh water rinse followed by air pressure drying. Light brushing with a stainless steel bristle brush during the fresh water rinse.

Recommendation to Customer: The ArmaKleen Technical Center recommended using 100% by volume ArmaKleen™ Paint and Ink Remover at 150°F in a Spray Under Immersion Washer for a minimum of 24 hours.

Before Picture



After Picture



Source: TSR #16-P-043