

ArmaKleen Technical Service Report Summary

Cleaning Trial Type: Paint & Ink

Industry: Lawn care

Segment: 86 – Entertainment and Recreation Services

Soil: Unknown paint

Substrate: Aluminum, plastic, steel, stainless steel, rubber

Description of Part(s): Nozzles

Customer objective: Improve cleaning performance

Cleaner used: 100% by volume solution of ArmaKleen™ Paint & Ink Remover

Machine used: Spray Under Immersion Washer (SK Model 81.8, Graymills T12, Graymills T24 w/ SUI)

Temperature used: 160°F

Time required: 16 hours

Post Cleaning: Fresh water rinse and air pressure drying

Recommendation to Customer: The ArmaKleen Technical Center recommends using a 100% by volume solution of ArmaKleen™ Paint and Ink Remover at 160°F in a Spray Under Immersion Washer for a minimum of 16 hours

Before Picture



After Picture



Source: TSR #17-P-190